Plasmonic Enhancement of Dye-Sensitized Solar Cells Using Core– Shell–Shell Nanostructures

Stafford W. Sheehan,[†] Heeso Noh,[‡] Gary W. Brudvig,^{*,†} Hui Cao,^{*,‡} and Charles A. Schmuttenmaer^{*,†}

[†]Department of Chemistry, Yale University, 225 Prospect St., PO Box 208107, New Haven, Connecticut 06520-8107, United States [‡]Department of Applied Physics, Yale University, New Haven, Connecticut 06511, United States

Supporting Information

ABSTRACT: We report the synthesis of core-shell-shell Au@SiO₂@TiO₂ nanostructures and demonstrate near-field plasmonic enhancement of dye-sensitized solar cells (DSSCs) incorporating them. Isolated nanoparticles as well as nanostructured plasmonic aggregates with broadband light absorption throughout the visible light region are developed. Comparisons to theoretical calculations are performed for the nanoparticles to provide further insight into their structure. We show that Au@SiO₂@TiO₂ nanoparticles provide efficiency enhancements greater than that of Au@SiO₂ plasmonic nanoparticles and vary the distance between the molecular chromophore and the gold NP surface to demonstrate that this



arises from near-field plasmonic effects. Finally, enhancement of dye absorption in DSSCs using a coupled plasmonic system is shown for the first time and results in a broadband enhancement of quantum efficiency.

INTRODUCTION

Nanostructures made of noble metals have long been used to manipulate light on a subwavelength scale. This has led to numerous applications in spectroscopy,¹ optics,² and many other fields.^{3,4} Solar cells in particular are dependent on efficient harnessing of light for conversion to electricity or chemical fuel, and this has recently opened the field of plasmonic enhancement applied to solar cells.^{5,6} Of the types of solar cells being researched, dye-sensitized solar cells (DSSCs) are a promising alternative to traditional solar cells and are particularly amenable to incorporation of plasmonic nanoparticles. Similar concepts can also be extended toward plasmonic enhancement of other types of solar cells, such as organic,⁷ silicon,⁵ and water-splitting systems.⁸ In order to best integrate them into a TiO₂ nanoparticle-based DSSC, we created a nanostructure comprised of a plasmonic Au nanoparticle encapsulated in a SiO₂ shell followed by a TiO₂ shell. The SiO₂ shell electronically insulates the Au core and also protects it from corrosion or other deleterious effects. The TiO₂ layer allows these NPs to be seamlessly incorporated into nanoscale mesoporous TiO2-based photoanodes used in dyesensitized photocatalytic or photoelectrochemical solar cells. It is essential that the SiO₂ and TiO₂ shells are thin enough that chromophores bound to the Au@SiO2@TiO2 nanoparticles experience near-field plasmonic enhancement.

Recent studies have shown that plasmonic enhancement is indeed a viable path toward improving DSSCs. Using plasmonics to concentrate light, it is possible to reduce the thickness of the mesoporous TiO_2 working electrode without hindering absorption.⁹ This reduces the distance charges must

travel to reach the external circuit and lessens the probability of charge recombination. The first technological hurdle to overcome in this design is that bare metallic nanoparticles are shown to both corrode and facilitate carrier recombination in DSSCs,¹⁰ requiring them to be insulated from the surrounding electrolyte.¹¹ Subsequent work incorporating an insulating SiO₂ shell around a metal nanoparticle provided a partial solution to this problem;¹² however, molecular dyes cannot inject charges into SiO₂, which reduces the potential effectiveness of the plasmonic nanoparticle. This issue of charge injection can be resolved by coating nanoparticles instead with TiO₂ before incorporating them into a DSSC, a strategy which has met with some success.⁹ However, chemical insulation of metal nanoparticles that does not also provide electrical insulation opens up the metal core to charging effects, which have been shown to increase the efficiency less than plasmonic effects.¹³ Plasmonic enhancement of DSSCs has also been demonstrated with both smaller¹⁴ and larger Au nanoparticles,¹⁵ Au@TiO₂ hollow submicrospheres,¹⁶ and Au@Ag₂S nanorods,¹⁷ though many issues remain unresolved.

In our demonstration, we utilize a new structure combining the advantage of an insulating SiO_2 coating with a photoconductive TiO_2 shell. The resulting multilayered nanoparticle provides a greater enhancement to DSSC performance compared to using single shells. We demonstrate this by building devices with thin working electrodes to show that our new approach overcomes the problems outlined previously. We

Received: December 10, 2012 Published: December 17, 2012

find the greatest improvements to device performance when nanostructures made by controlled aggregation of Au@SiO₂ nanoparticles were added to a DSSC. We attribute this to both the broadband absorption of these structures^{18–20} and the larger dipole moments brought about by coupled surface plasmon resonance modes.^{19,21}

Gold was chosen as a metallic core for our system because the localized surface plasmon resonance (LSPR) in Au nanoparticles (NPs) occurs in the vicinity of 525 nm. Furthermore, the peak wavelength of the LSPR increases as the refractive index of the surrounding medium increases.^{22–24} Thus, it is possible to achieve a maximum in the nanoparticle's extinction spectrum near the maximum absorbance of the most commonly used dye for DSSCs, N719, at 530 nm. While the peak position of the LSPR is barely dependent on the Au NP radius in the range 5–20 nm, the near-field plasmonic enhancement increases significantly with decreasing particle size.⁴

On the basis of the considerations given above, we have synthesized spherical Au NPs with a 9 nm radius and added a SiO_2 shell roughly 1.6 nm thick. We compare the performance when growing TiO_2 shells that are ~2.5 and ~7.0 nm thick. The optical properties of solutions of these NPs depend on the nature of the shell(s) and surrounding medium and are successfully simulated.

We constructed DSSCs consisting of sintered P25 TiO₂ NPs sensitized with N719 using an I_3^-/I^- redox shuttle and compared their performance in the absence and presence of Au@SiO₂, Au@SiO₂@TiO₂ with both thin and thick TiO₂ layers, and Au@SiO₂@TiO₂ aggregates. The DSSC efficiency increases when incorporating each type of these plasmonic NPs and does so most dramatically for the ones with a thin TiO₂ shell and the aggregates.

One general advantage of incorporating nanoparticles into DSSCs is that they provide far-field scattering and concomitant enhancement due to longer effective optical path lengths.⁵ There have been previous reports of incorporating metal core@ shell NPs into DSSCs, where the metal core is Au or Ag and the shell is SiO₂ or TiO₂.^{9,12-14,25} There have also been theoretical studies of multilayered structures,²⁶ but no experimental data as of yet. Encapsulating metal NPs in a shell serves three purposes: (1) If the shell is an insulator, it can electrically insulate the Au NP from its surroundings. This is important because bare Au NPs trap electrons and facilitate reduction of I_3^- to I⁻ thereby acting as a loss mechanism.¹² (2) It is possible to grow very thin shells that allow the dye molecules to be in close enough proximity to the metal NP for plasmonic enhancement. (3) The shell provides a physical barrier to the I_3^- which is corrosive toward Au.^{27,28}

Rather than utilizing a single shell, we chose the core@ shell@shell architecture to benefit from both types of shells. Specifically, if the TiO₂ layer is not used, then the dye molecules most influenced by the plasmonic enhancement are physisorbed rather than chemisorbed on the SiO₂ shell, and its band gap is too large to allow electron injection. We note, however, that improvements have been reported for this structure nonetheless.^{12,13} This is due to dye molecules bonded to TiO₂ NPs in the mesoporous network that happen to be in close proximity to the Au@SiO₂ NPs. However, when a TiO₂ shell is grown on top of the SiO₂ shell as is reported here, electrons can be injected directly into the TiO₂ shell that incorporates the NPs into the photoanode. Very thin shells are required since the near-field plasmonic enhancement decreases rapidly as a function of distance from the Au surface, 29,30 and it is shown here that the thin TiO₂ shell outperforms the thick one.

Finally, we find that Au@SiO₂@TiO₂ aggregates provide the highest increase in DSSC efficiency. This is attributed to two factors: (1) The localized surface plasmons in individual particles are coupled to form surface plasmon resonances over a broad frequency range, thus enhancing light absorption over a wider frequency range than isolated NPs.³¹ (2) Most of the coupled surface plasmon resonances have larger dipole moments than those of a single NP, producing a higher local field.^{32–36}

EXPERIMENTAL METHODS

Au nanoparticles with a thin SiO₂ shell were synthesized following previously published methods.^{12,22} To synthesize the Au core, the Turkevich method was employed.³⁷ A solution of 0.02% w/w hydrogen tetrachloroaurate (III) trihydrate in deionized water (150 mL) was heated to boil, to which 6.5 mL of a solution of 1% w/w citric acid (trisodium salt dihydrate) was added while stirring. The solution rapidly turned black and after ~75 s became a dark red-orange color which indicated the formation of Au nanoparticles. The solution was boiled for an additional 15 min to ensure that the reaction proceeded to completion and was then removed from the heat and allowed to cool to room temperature.

To grow conformal SiO₂ shells, the citrate adsorbate surrounding the Au nanoparticles was exchanged with 3aminopropyltriethoxysilane (APTES) by adding 1.5 mL of a 1.92 μ M APTES solution dropwise over 30 min while vigorously stirring. The solution sat without stirring for an additional 30 min before addition of 5.5 mL of 0.54% w/w sodium silicate with pH reduced to 10.26 using a Dowex HCR-S cation-exchange resin. This solution then sat for 36 h, allowing the SiO₂ shells to grow before being centrifuged at 3150 rpm (Fischer, 614b) and redispersed via sonication into 200 proof ethanol, thereby ending shell growth.

Synthesis of TiO₂ shells on these Au@SiO₂ nanoparticles followed methods previously described for TiO_2 shell growth with small modifications.^{9,38} For thinner shells (roughly 2.5 nm), 1 mL of 4% ammonia in ethanol was added to 10 mL of Au@SiO2 nanoparticles at 1.5 times their original concentration. 5 μ L of Ti[OHC(CH₃)₂]₄, denoted Ti(OⁱPr)₄, in 3 mL of ethanol was then added to the solution, which was stirred for 12 h and then sonicated for 30 min. 15 μ L of Ti(OⁱPr)₄ was hydrolyzed in 1 mL of 95% ethanol and added to the nanoparticle solution while sonicating to ensure that the same amount of Ti(OⁱPr)₄ was added to both thin and thick shell solutions. For thicker shells (roughly 7.0 nm), 1 mL of 4% ammonia in ethanol was added to 10 mL of Au@SiO₂ nanoparticles at 1.5 times their original concentration, after which 5 μ L of Ti(O'Pr)₄ in 1 mL of ethanol was slowly added to begin a thin shell growth. 10 mg of hydroxypropyl cellulose was slowly added to the solution, which was stirred for 1 h and then sonicated for 15 min. Another 5 μ L of Ti(O^{*i*}Pr)₄ in 1 mL of ethanol was added to the solution, and it was stirred for 30 min, followed by sonication for 5 min. This process was repeated two more times such that a total of 20 μ L of Ti(O^{*i*}Pr)₄ was added to the solution, and the nanoparticle solution was then stirred for 12 h. The samples with 2.5 and 7.0 nm TiO₂ layers are referred to as "Au@SiO2@TiO2 (thin)" and "Au@ SiO_2 (thick)", respectively.

In order to form random nanoparticle aggregates, the concentration of $Au@SiO_2$ nanoparticles in ethanol was doubled via centrifugation and then sonicated for 15 min. 20 mL of the concentrated nanoparticle solution was vigorously stirred while 1 mL of ethanol containing 10 μ L of Ti(OⁱPr)₄ was rapidly added to it. The solution changed color from red to bluish-purple. Within the next 2 h, the solution continued darkening until it turned pitch black, signifying formation of the nanostructures. Vigorous stirring or sonication is required in order to aerate the solution and introduce a small amount of water into the dry ethanol, allowing the titanium precursor to hydrolyze sufficiently to form aggregates. While a TiO₂ layer was not intentionally grown on them, a very thin and nonuniform layer forms when the Ti(OⁱPr)₄ is added to induce aggregation (Figure S1).

Synthesis of Pt counter electrodes and I_3^{-}/I^{-} electrolyte solution for solar cells followed a previously published procedure.³⁹ In order to make a plasmonic TiO₂ paste used in doctor-blading onto fluorine-doped tin oxide (FTO) for DSSC photoanodes and glass microscope slide coverslips for UV-vis measurements, 0.1 mL of 1% acetic acid in water was added to 2 mL of nanoparticle solution and sonicated for 10 min. P25 TiO₂ nanoparticles (Evonik/Degussa) were slowly added during sonication to ensure paste homogeneity. 500 mg of P25 per 2 mL of ethanol solution was added to pastes without nanoparticles and with Au@SiO2 nanoparticles, while 250 mg of P25 was used per 2 mL of TiO₂-shelled nanoparticle solutions. Pastes were then carefully doctor-bladed onto coverslips and FTO using a 0.25 cm² template for the working electrode active area. This yielded films approximately 10-12 μ m thick. After coating, samples were heated to 400 °C for 2 h to allow particle sintering without the formation of rutile in the TiO₂ shells. After sintering, the nanoparticles were immersed in a 0.2 mM ethanol solution of N719 dye [ditetrabutylammonium cis-bis(isothiocyanato)bis(2,2'-bipyridyl-4,4'dicarboxylato)ruthenium(II)] for 24 h.

Characterization of the nanoparticles was carried out using scanning electron microscopy (SEM), transmission electron microscopy (TEM), and UV–vis spectrophotometry. Low-resolution TEM images were taken using a Zeiss EM-900 operating at 80 kV while high-resolution TEM images and scanning TEM/energy dispersive X-ray (STEM/EDX) mapping was performed using an FEI Tecnai Osiris operating at 200 kV. A Hitachi SU-70 was used to take SEM images. UV–vis measurements were taken using a Varian Cary 3 spectrophotometer. Spectra of dyed samples on microscope slide coverslips were determined with an integrating sphere in diffuse reflectance mode by measuring transmittance and reflectance separately and then calculating the absorptance using A = 1 - R - T.

DSSCs were assembled using a 60 μ m plastic thermal spacer (SX1170-60, Solaronix SA, Switzerland) to contain the electrolyte by sandwiching it between the electrodes and held together with metal binder clips. Photocurrent–voltage scans were taken using a Keithley 2400 source meter, and a 300 W ozone-free xenon lamp equipped with an AM 1.5G filter (Newport) was used as the light source. The light intensity was adjusted to 1-sun conditions (100 mW/cm²) prior to scanning. Incident photon-to-current efficiency (IPCE) measurements were made with a PV Measurements Inc. Solar Cell Spectral Response Measurement System (Model QEXY), calibrated between 300 and 1000 nm using a silicon photodiode. A chopping speed of 5 Hz was used during both calibration and

measurement. Exact TiO_2 photoanode areas were determined using a 1200 dpi scanner.

RESULTS AND DISCUSSION

The SiO₂ shell was grown as thin as possible without the formation of holes or significant loss of surface coverage as determined by TEM imaging. The near-field nature of LSPR and the fact that the TiO_2 outer shell must be thick enough to allow facile charge transfer and transport render a thin SiO₂ shell critically important. The slow growth afforded by lowering the pH of the sodium silicate precursor and controlling its concentration ensures that the shell is as conformal as possible. Figures 1a and 1b show Au nanoparticles before and after



Figure 1. Citrate-stabilized gold nanoparticles (a), along with nanoparticles from the same batch after coating with silica (b), then further with a thin titania coating (\sim 2.5 nm) (c), and thick titania coating (\sim 7.0 nm) (d). Scale bars are all 50 nm.

growth of the SiO₂ shell, respectively. The thickness of the shell is \sim 1.6 nm. While some tunneling may occur, we found when incorporating them in to solar cells that the majority of electronic communication between TiO₂ and Au was inhibited.

Growth of the TiO_2 shell also required pH control of the solution by a low concentration of ammonia in ethanol. If concentrations were too low, nanoparticles were prone to aggregate together rather than simply grow TiO_2 shells. As shown in Figures 1c and 2a, the thin TiO_2 shells are typically quite jagged which may provide more surface area for dye coverage but can also impede electron transport. Thicker TiO_2 shells were also grown (Figure 1d) and have smoother surfaces in addition to their increase in overall thickness. Dimensions of the Au NPs and metal oxide shell(s) were obtained by image analysis of 100 NPs of each type and are given in Table S1.

TEM, EDX, and STEM/EDX mapping were used to confirm the morphology of the Au@SiO₂@TiO₂ nanostructures. Figure 2a is a HRTEM image of a dual-shelled nanoparticle with a smooth SiO₂ layer, covered by a jagged TiO₂ layer, and Figure 2b shows an EDX map of nanoparticles which clearly reveal a gold core (green) surrounded by a SiO₂ shell (blue), which is then encapsulated by TiO₂ (red). Additional EDX spectra,



Figure 2. (a) HRTEM image of an Au@SiO₂@TiO₂ (thin) NP showing both inner SiO₂ and outer TiO₂ shells; scale bar: 5 nm. (b) STEM-EDX map of Au@SiO₂@TiO₂ (thin) NPs showing an Au core (Au shown in green), a conformal SiO₂ inner shell (Si shown in blue), and a jagged TiO₂ outer shell (Ti shown in red); scale bar: 30 nm.

TEM images, and characterization of the NPs and aggregates are included in the Supporting Information.

Experimental and calculated UV–vis extinction spectra for Au and Au@SiO₂ NPs in water and Au@SiO₂@TiO₂ (thin) NPs and aggregates in ethanol are shown in Figure 3. Mie



Figure 3. Experimental (solid lines) and calculated (dashed lines) UV–vis spectra of nanoparticles in solution showing a red shift in plasmon resonance peak position as shells are added. APTES-stabilized Au NPs, Au@SiO₂ NPs, and Au@SiO₂@TiO₂ (thin) NPs are represented by black, red, and blue traces, respectively. The purple curve at the bottom shows the absorption spectrum of N719 for comparison. Inset: absorption spectrum of nanostructured aggregates formed from Au@SiO₂ NPs, showing broadband absorption of visible light.

theory is used to calculate the spectra⁴⁰ using the wavelengthdependent complex refractive index of bulk Au^{41} and are in excellent agreement with the measured spectra. Refractive indices for SiO₂ and TiO₂ of 1.461 and 2.488 were used, respectively, and assumed to be constant over the frequency range of interest. Similarly, the refractive indices of water and ethanol were held fixed at 1.333 and 1.361, respectively.

The calculated peak width is too narrow when only free electron scattering in the bulk metal is assumed. However, as the NP size approaches the mean free path of free electrons in Au, the scattering rate increases⁴² and the value of the dielectric

constant changes. Specifically, the frequency-dependent dielectric function, ε , is given by⁴³

$$\varepsilon(\omega) = \varepsilon_{\rm B}(\omega) + \varepsilon_{\rm D}(\omega) \tag{1}$$

The frequency is denoted ω , $\varepsilon_{\rm B}(\omega)$ is due to bound electrons, and $\varepsilon_{\rm D}(\omega)$ is due to free electrons which are assumed to obey Drude behavior. Furthermore, the Drude term is expressed as⁴³

$$\epsilon_{\rm D}(\omega) = 1 - \frac{\omega_{\rm p}^2}{\omega^2 + i\gamma\omega} \tag{2}$$

where γ is the damping coefficient and $\omega_{\rm p}$ is the plasmon frequency $\omega_{\rm p} = ne^2/\varepsilon_0 m_{\rm eff}$ (*n* is the electron density, *e* is the magnitude of the electron charge, ε_0 is the permittivity of free space, and $m_{\rm eff}$ is the electron effective mass). In the bulk, the damping coefficient γ is given by $\gamma_0 = v_{\rm F}/l_{\infty}$, where $v_{\rm F}$ is the Fermi velocity and l_{∞} is the bulk mean free path.⁴⁴ In a NP, the damping coefficient depends on particle size, and for a spherical particle with isotropic scattering it becomes⁴³

$$\gamma_{\rm R} = \gamma_0 + \frac{Av_{\rm F}}{R} \tag{3}$$

where *A* is a dimensionless parameter typically near unity and *R* is the NP radius. Thus, the bulk complex permittivity values, $\varepsilon_{\text{bulk}}$, from ref 41 (obtained from $\varepsilon' = n^2 - k^2$ and $\varepsilon'' = -2nk$, since $n^2 = \varepsilon$) are corrected for the additional scattering term using

$$\varepsilon_{\rm NP}(\omega, R) = \varepsilon_{\rm bulk} - \left(1 - \frac{\omega_{\rm p}^2}{\omega^2 + i\gamma_0\omega}\right) + \left(1 - \frac{\omega_{\rm p}^2}{\omega^2 + i\gamma_{\rm R}\omega}\right)$$
(4)

The value of A is fixed at $(\pi/2)^{1/3}$, or 1.16, for the calculated spectra in Figure 3.⁴² The SiO₂ and TiO₂ shells red-shift the localized surface plasmon resonance; the TiO₂ shell shifts it by a greater amount than SiO₂ because the difference between its refractive index and that of the surrounding medium is greater than for SiO₂. The average SiO₂ shell thickness is determined to be 1.6 nm from TEM images. There is a bit of porosity, however, so its effective refractive index, $n_{\rm eff}$, is smaller than the bulk value and is given by⁴⁵

$$n_{\rm eff} = \sqrt{f \varepsilon_{\rm MO_2} + (1 - f) \varepsilon_{\rm m}} \tag{5}$$

where ε_{MO_2} is the permittivity of the metal oxide, *f* is its volume fraction, and ε_m is fixed at 1.0. A 92% volume fraction of SiO₂ in the shell results in excellent agreement between the calculated and measured peak position of Au@SiO₂ NPs in water. Similarly, we compared the calculated extinction spectrum of Au@SiO₂@TiO₂ NPs in ethanol to the measured one. In this case, the peak center moves to 634 nm, and the volume fraction of TiO₂ in the 2.5 nm shell is 65%. The relatively low volume fraction is partly due to the nonuniform thickness of the TiO₂ shell.

The aggregate nanostructures have broadband absorption throughout the visible spectral region due to coupled plasmon modes, which results in their deep black color (a photograph is shown in Figure S7). The absorption is broadband due to a large distribution in interparticle distances among the randomly aggregated particles,¹⁹ in addition to small variations in SiO₂ shell thickness and excess TiO₂ used to form them.

The DSSCs constructed were found to have a uniform dispersion of NPs throughout their working electrodes. Figure 4 is an edge-on SEM micrograph of a 12 μ m thick doctor-



Figure 4. SEM image of a P25 TiO₂ film on FTO/glass with Au@SiO₂ NPs embedded. Scale bar: 5 μ m.

bladed film with Au@SiO2 NPs incorporated; Au@SiO2 NPs tend to appear with a higher contrast than P25 TiO₂. Relative concentrations of NPs are represented in Figure S4, which shows the absorptance spectra (1 - R - T) of doctor-bladed films before being immersed in dye. The films are \sim 0.1% w/w Au, which is a typical concentration for which plasmonic enhancement is seen in DSSCs.¹² Figure 5a compares IPCE results for DSSCs incorporating Au@SiO2, Au@SiO2@TiO2 (thin), Au@SiO2@TiO2 aggregates, and one that does not contain any NPs. It is seen that all of the samples with NPs perform better than those without. The Au@SiO₂@TiO₂ samples perform better than the Au@SiO2 ones, and the aggregates provide the highest IPCE of all. The peak of the IPCE curve does not shift significantly for the different samples, which is consistent with their UV-vis absorbance spectra. It is important to note that the LSPR modes of the nanoparticles have been matched to the N719 peak absorption wavelength through their size control and choice of gold over silver. In addition, the aggregates couple with the dye at wavelengths longer than the peak value of 530 nm, which is due to the dye interacting with the coupled LSPR modes of multiple metal nanoparticles in the aggregates.

Figure 5b displays their absorptance spectra after being immersed in N719 dye, and it is seen that they follow the same general trend as the IPCE curves except for the aggregates at wavelengths longer than 700 nm. At these wavelengths, the aggregates themselves absorb light but the dye sensitizer does not, so electrons will not be injected into the semiconductor and thus will not contribute to the IPCE. Careful inspection reveals that this also occurs to a lesser extent with the Au@SiO₂ and Au@SiO₂@TiO₂ (thin) samples. It is seen that NPs enhance the maximum IPCE by a factor of 1.2–1.6 and the maximum absorptance by a factor of 1.2–1.5.

Current–voltage (J-V) curves were measured for DSSCs that were constructed without any metal NPs, those incorporating Au@SiO₂, with Au@SiO₂@TiO₂ (thin), Au@SiO₂@TiO₂ (thick), and aggregates. Nine samples of each type were made. The best one of each type is shown in Figure 6a, and the averages are shown in Figure 6b. The usual solar cell parameters of open-circuit voltage, V_{oct} short-circuit current, J_{sct} fill factor, and efficiency are reported in Table 1, while standard deviations are reported in Table S2 and are plotted together in Figure S8.

P25 TiO₂ dispersed in ethanol without any metal nanoparticles and doctor-bladed onto the substrate resulted in highly porous films ~12 μ m thick. After being immersed in the N719 dye solution, the films remained moderately transparent, as shown in Figure 5b. This partially accounts for their low DSSC efficiency compared to films made using additional preparation procedures such as TiCl₄ treatments, thicker active layers, optimization of TiO₂ paste, and light-scattering layers,⁴⁶ which we omitted in this initial proof of concept.

Addition of Au@SiO₂ nanoparticles to the TiO₂ paste during fabrication increases J_{sc} and the efficiency due to plasmonic enhancement, as has been seen in previous studies.^{12,13} The DSSCs made from Au@SiO₂@TiO₂ (thin) and the aggregates have the best efficiencies and J_{sc} values.

The DSSC incorporating the aggregates is the first demonstration of enhancement of efficiency using plasmonic nanoparticles coupled with each other (in addition to the surrounding dye). In this case, the enhancement in overall efficiency is a result of an increase in both $V_{\rm oc}$ and $J_{\rm sc}$. This may be a contribution from the high electromagnetic fields caused by the coupled plasmonic modes in the aggregates because the coupled surface plasmon modes typically have larger dipole moments than the uncoupled ones in isolated NPs.^{21,33} Overall, the aggregates improve the efficiency of these DSSCs from



Figure 5. IPCE (a) and absorptance spectra (b) with different plasmonic NPs embedded in TiO_2 electrodes containing ~0.1% w/w Au. Measurements were made on samples with efficiencies most similar to their "average" in Table 1.

Article



Figure 6. J-V curves for solar cells made with no NPs in P25 TiO₂ (black), Au@SiO₂ (red), Au@SiO₂@TiO₂ thin (purple), Au@SiO₂@TiO₂ thick (blue), and aggregates (maroon). (a) shows the best solar cells incorporating each type of nanoparticle, while (b) depicts an average of the nine curves in each batch.

Table 1. Averages for Each Parameter Contributing to Solar Cell Efficiency in Addition to Best Efficiency Values; Total Shell Thicknesses for the Nanoparticles Are Included in Parentheses

nanoparticles in P25	$V_{ m oc}$ (V)	$J_{\rm sc}$ (mA/cm ²)	FF (%)	av efficiency (%)	best efficiency (%)
none	0.746	6.64	56.8	2.81	3.07
Au@SiO ₂ (1.6 nm)	0.753	7.78	60.3	3.52	4.04
Au@SiO ₂ @TiO ₂ (4.1 nm)	0.773	9.37	57.0	4.02	4.60
Au@SiO ₂ @TiO ₂ (8.6 nm)	0.754	6.81	58.2	2.99	3.54
aggregates	0.804	11.59	59.3	5.52	6.42

2.81% (no metal NPs) to 5.52%. This is the largest reported improvement of DSSC absolute efficiency due to plasmonic enhancement to our knowledge and the first demonstration of using a coupled plasmonic system to improve a DSSC.

The DSSCs with Au@SiO₂@TiO₂ (thick) NPs perform very similarly to the standard DSSC without any NPs at all (Figure 6b). They are identical to those containing Au@SiO2@TiO2 (thin) NPs except that the SiO₂ and TiO₂ combined shell thickness is 8.6 nm compared to 4.1 nm for the thin-shelled NPs. This demonstrates that the enhancement when using Au@SiO₂@TiO₂ (thin) is a near-field plasmonic effect since it is extremely sensitive to distance from the Au metal core. The DSSCs with Au@SiO2@TiO2 (thick) NPs have a slightly higher efficiency than those without any NPs at all, which indicates a small amount of far-field plasmonic enhancement due to scattering. Roughness of the outer TiO₂ shell also plays a role in performance of the samples containing thick vs thin TiO₂ shells. The thin TiO₂ shells have higher roughness than the thick ones, which results in a larger surface area for dye adsorption. More importantly, the molecules found at the bottom of the shallow regions experience much stronger plasmonic near-field enhancement.

It is useful to model the DSSC behavior to better understand the underlying changes that affect the measured cell parameters $(V_{oc}, J_{sc}, \text{fill factor, and efficiency})$. The standard description of a diode solar cell has been applied successfully to DSSCs by many authors and is given by⁴⁷

$$J = J_{\rm L} - J_{\rm D} - J_{\rm SH}$$
$$J = J_{\rm L} - J_0 \left\{ \exp\left[\frac{q(V + JAR_{\rm S})}{fk_{\rm B}T}\right] - 1 \right\} - \frac{V + JAR_{\rm S}}{AR_{\rm SH}}$$
(6)

where J is the net current density, J_L is the photocurrent density, J_0 is the reverse saturation current density, V is the applied voltage, R_S and R_{SH} are the series resistance and shunt resistance of the cell, respectively, A is the area of the cell, q is the magnitude of the electron charge, $k_{\rm B}$ is Boltzmann's constant, f is the ideality factor (which is fixed at 2), and T is the temperature, which is fixed at 298 K. The series resistance arises from resistances of the photoanode, transparent conducting electrodes, and electrolyte solution. Higher values of $R_{\rm S}$ decrease the cell efficiency primarily by decreasing the fill factor but also to a lesser extent through a reduction in $J_{\rm sc}$. Smaller values of R_{SH} allow the parasitic shunt current, J_{SH} , to increase which degrades the overall performance, primarily through a decrease in the fill factor. The shunt current arises from losses due to carrier recombination with the oxidized dye molecule and/or direct recombination with the redox couple.

This model was fit to the experimental J-V curves for the best devices and for the average performance. The agreement between the model and the experimental data is quite good as seen in Figure S9, and the parameters obtained are given in Table S3. The overall trends in DSSC performance are dominated by the behavior of J_{1} , but J_{0} also plays a minor role. $R_{\rm S}$ and $R_{\rm SH}$ have much smaller influence. If there is a decrease in the reverse saturation current, J_0 , which is due electrons traveling "backwards" from the conduction band to the excited state energy level of the dye molecules, then $V_{\rm oc}$ will increase with no change in J_{sc} . An increase in J_L , which is caused by higher electron injection rates, will simply shift the entire J-V curve upward (as long as R_S is small and R_{SH} is large, as is the case here), causing both $J_{\rm sc}$ and $V_{\rm oc}$ to increase. There is an additional limit regarding how much $V_{\rm oc}$ may increase since it can be no larger than the difference between the TiO₂ Fermi level and the I_3^{-}/I^{-} reduction potential. Since the aggregates have significantly higher values of J_L due to interparticle plasmonic coupling, they significantly outperform the other samples.

CONCLUSION

In summary, we have synthesized a new type of nanostructure using a metal-insulator-semiconductor design to insulate and protect plasmonic nanoparticles while simultaneously incorporating a photoactive semiconductor as its outermost layer. In addition, we constructed a metal-insulator aggregate system, which allows nanoparticles to couple with each other forming LSPR modes that show broadband absorption throughout the visible light region.

We have shown that the metal-insulator-semiconductor nanoarchitecture can be successfully incorporated into DSSCs to yield improvements beyond those of a metal-insulator system due to the closer proximity of dye molecules to the metal surface. We have demonstrated quenching of the plasmonic enhancement by increasing the semiconductor shell thickness, thereby establishing that the enhancement arises from near-field effects, namely LSPR modes. Broadband enhancement of dye absorption in DSSCs is shown using a coupled plasmonic system resulting in an increase in efficiency from 2.81% to 5.52% on average when compared to those made without metal nanoparticles. After this initial proof of concept, our future studies will include optimizing and incorporating these black plasmonic aggregates into higher efficiency DSSCs.

The Au@SiO₂@TiO₂ architecture is amenable to other types of solar cells by using a different semiconductor for the active layer or by inducing aggregation with materials other than TiO₂. In addition, the broadband plasmonic enhancement afforded by the aggregates can be used in other spectroscopic applications, such as fluorescence, Raman scattering, and second harmonic generation.⁴⁸

ASSOCIATED CONTENT

S Supporting Information

TEM characterization of aggregates, EDX spectra and additional STEM-EDX maps, schematic of integrating sphere showing T and R modes, absorptance of working electrodes before immersion in dye, photographs of nanoparticles and aggregates, calculated best fits of eq 6 to experimental J-Vcurves, and additional solar cell characterization details. This material is available free of charge via the Internet at http:// pubs.acs.org.

AUTHOR INFORMATION

Corresponding Author

*E-mail: charles.schmuttenmaer@yale.edu (C.A.S.); hui.cao@ yale.edu (H.C.); gary.brudvig@yale.edu (G.W.B.).

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

We acknowledge the Yale Climate and Energy Institute (YCEI) and an NSF Graduate Research Fellowship for support of this work. We thank Stephanie Tomasulo and Prof. Larry Lee for helpful discussions and technical assistance with IPCE measurements and Dr. Michael Rooks for technical assistance gathering STEM-EDX data. Facilities use was supported by the Yale Institute for Nanoscience and Quantum Engineering (YINQE) and NSF MRSEC DMR 1119826.

REFERENCES

(1) Willets, K. A.; Van Duyne, R. P. Annu. Rev. Phys. Chem. 2007, 58, 267–297.

- (2) Kreibig, U.; Vollmer, M. Optical Properties of Metal Clusters; Springer-Verlag: Berlin, 1995.
- (3) Ihara, M.; Tanaka, K.; Sakaki, K.; Honma, I.; Yamada, K. J. Phys. Chem. B 1997, 101, 5153–5157.
- (4) Kelly, K. L.; Coronado, E.; Zhao, L. L.; Schatz, G. C. J. Phys. Chem. B 2003, 107, 668–677.
- (5) Atwater, H. A.; Polman, A. Nat. Mater. 2010, 9, 205-213.

(6) Ding, I. K.; Zhu, J.; Cai, W. S.; Moon, S. J.; Cai, N.; Wang, P.; Zakeeruddin, S. M.; Gratzel, M.; Brongersma, M. L.; Cui, Y.; McGehee, M. D. *Adv. Energy Mater.* **2011**, *1*, 52–57.

(7) Kim, S. S.; Na, S. I.; Jo, J.; Kim, D. Y.; Nah, Y. C. Appl. Phys. Lett. 2008, 93, 073307.

(8) Warren, S. C.; Thimsen, E. Energy Environ. Sci. 2012, 5, 5133-5146.

(9) Qi, J. F.; Dang, X. N.; Hammond, P. T.; Belcher, A. M. ACS Nano **2011**, *5*, 7108–7116.

(10) Peh, C. K. N.; Le, K.; Ho, G. W. Mater. Lett. 2010, 64, 1372-1375.

(11) Standridge, S. D.; Schatz, G. C.; Hupp, J. T. J. Am. Chem. Soc. 2009, 131, 8407-8409.

(12) Brown, M. D.; Suteewong, T.; Kumar, R. S. S.; D'Innocenzo, V.; Petrozza, A.; Lee, M. M.; Wiesner, U.; Snaith, H. J. *Nano Lett.* **2011**, *11*, 438–445.

(13) Choi, H.; Chen, W. T.; Kamat, P. V. ACS Nano 2012, 6, 4418-4427.

(14) Hou, W. B.; Pavaskar, P.; Liu, Z. W.; Theiss, J.; Aykol, M.; Cronin, S. B. Energy Environ. Sci. 2011, 4, 4650-4655.

(15) Nahm, C.; Choi, H.; Kim, J.; Jung, D. R.; Kim, C.; Moon, J.; Lee, B.; Park, B. *Appl. Phys. Lett.* **2011**, *99*, 253107.

(16) Du, J.; Qi, J.; Wang, D.; Tang, Z. Y. Energy Environ. Sci. 2012, 5, 6914–6918.

(17) Ching, S.; Li, Q.; Xiao, X.; Wong, K. Y.; Chen, T. *Energy Environ. Sci.* **2012**, *5*, 9444–9448.

(18) Jain, P. K.; El-Sayed, M. A. Chem. Phys. Lett. 2010, 487, 153–164.

(19) Esteban, R.; Taylor, R. W.; Baumberg, J. J.; Aizpurua, J. Langmuir 2012, 28, 8881-8890.

(20) Zook, J. M.; Rastogi, V.; MacCuspie, R. I.; Keene, A. M.; Fagan, J. ACS Nano **2011**, 5, 8070–8079.

(21) Shalaev, V. M.; Botet, R.; Tsai, D. P.; Kovacs, J.; Moskovits, M. *Physica A* **1994**, 207, 197–207.

(22) Liz-Marzan, L. M.; Giersig, M.; Mulvaney, P. Langmuir 1996, 12, 4329-4335.

(23) Underwood, S.; Mulvaney, P. Langmuir 1994, 10, 3427-3430.

(24) Chen, H. J.; Kou, X. S.; Yang, Z.; Ni, W. H.; Wang, J. F. Langmuir 2008, 24, 5233-5237.

(25) Jeong, N. C.; Prasittichai, C.; Hupp, J. T. Langmuir 2011, 27, 14609-14614.

(26) Chen, H.; Blaber, M. G.; Standridge, S. D.; DeMarco, E. J.; Hupp, J. T.; Ratner, M. A.; Schatz, G. C. J. Phys. Chem. C 2012, 116, 10215–10221.

(27) Davis, A.; Tran, T.; Young, D. R. Hydrometallurgy 1993, 32, 143–159.

(28) Standridge, S. D.; Schatz, G. C.; Hupp, J. T. *Langmuir* **2009**, *25*, 2596–2600.

(29) Lal, S.; Grady, N. K.; Goodrich, G. P.; Halas, N. J. Nano Lett. 2006, 6, 2338–2343.

(30) Funston, A. M.; Novo, C.; Davis, T. J.; Mulvaney, P. Nano Lett. 2009, 9, 1651–1658.

(31) Rand, B. P.; Peumans, P.; Forrest, S. R. J. Appl. Phys. 2004, 96, 7519-7526.

(32) Markel, V. A.; George, T. F. Optics of Nanostructured Materials; Wiley: New York, 2001.

(33) Sarychev, A. K.; Shalaev, V. M. Phys. Rep. 2000, 335, 275-371.

(34) Seal, K.; Genov, D. A.; Sarychev, A. K.; Noh, H.; Shalaev, V. M.; Ying, Z. C.; Zhang, X.; Cao, H. *Phys. Rev. Lett.* **2006**, *97*, 206103.

(35) Seal, K.; Sarychev, A. K.; Noh, H.; Genov, D. A.; Yamilov, A.;

Shalaev, V. M.; Ying, Z. C.; Cao, H. Phys. Rev. Lett. 2005, 94, 226101.

(36) Schuller, J. A.; Barnard, E. S.; Cai, W. S.; Jun, Y. C.; White, J. S.; Brongersma, M. L. *Nat. Mater.* **2010**, *9*, 193–204.

(37) Enustun, B. V.; Turkevich, J. J. Am. Chem. Soc. 1963, 85, 3317–3328.

(38) Lee, J. W.; Kong, S.; Kim, W. S.; Kim, J. Mater. Chem. Phys. 2007, 106, 39-44.

(39) Moore, G. F.; Konezny, S. J.; Song, H. E.; Milot, R. L.; Blakemore, J. D.; Lee, M. L.; Batista, V. S.; Schmuttenmaer, C. A.; Crabtree, R. H.; Brudvig, G. W. *J. Phys. Chem. C* **2012**, *116*, 4892–4902.

(40) Pena, O.; Pal, U. Comput. Phys. Commun. 2009, 180, 2348-2354.

(41) Johnson, P. B.; Christy, R. W. Phys. Rev. B 1972, 6, 4370-4379.

(42) Kraus, W. A.; Schatz, G. C. J. Chem. Phys. 1983, 79, 6130-6139.

(43) Coronado, E. A.; Schatz, G. C. J. Chem. Phys. 2003, 119, 3926–3934.

(44) Values of Drude parameters are taken from Reference 23: $\omega_{\rm p}{=}$ 1.44 \times 10¹⁶ s⁻¹, $\gamma_0{=}$ 1.075 \times 10¹⁴ s⁻¹, $v_{\rm F}{=}$ 1.4 \times 10⁶ m/s, and $l_{\infty}{=}$ 13.0 nm.

(45) Soukoulis, C. M.; Datta, S.; Economou, E. N. Phys. Rev. B 1994, 49, 3800-3810.

(46) Ito, S.; Chen, P.; Comte, P.; Nazeeruddin, M. K.; Liska, P.; Pechy, P.; Gratzel, M. Prog. Photovoltaics **2007**, *15*, 603–612.

(47) Elguibaly, F.; Colbow, K.; Funt, B. L. J. Appl. Phys. 1981, 52, 3480-3483.

(48) Shalaev, V. M. Nonlinear Optics of Random Media: Fractal Composites and Metal-Dielectric Films; Springer: Berlin, 2000.